



### **Duracoat Duraplast DDE 3**

#### **Product Description:**

Duracoat Duraplast is a special quality emulsion paint manufactured from acrylic resin and high quality pigments. It is formed to give long term protection for interior, exterior and masonry walls. It contains a special fungicide that makes it potent to mould and algae. Duracoat Duraplast is formulated for use around coastal regions and areas subject to severe tropical weather conditions.

#### **Finish:**

Matt with a beautiful low sheen and smooth finish

#### **Application:**

Brush, roller or conventional spray

#### **Thinning:**

Use clean water, up to 15% on first coat and up to 10% on subsequent coats. On new and porous surfaces, thin the first coat with clean water to ease brushing. **DO NOT overthin.** 2-3 coats are recommended for best results.

#### **Drying Time:**

Touch dry: 10-15 minutes. Recoating time: 4-6 hours in fair weather condition.

#### **Cleaning:**

Clean equipment with water.

#### **Colour:**

A wide range of shades available from the Duracoat colour chart, Duracoat Classic and Colour Plus fandecks.

#### **Spread Rate:**

13-14 sq.m/litre when applied to non-porous smooth surfaces. On cement rendered surfaces, 10-11 sq.m/litre. Coverage is considerably reduced when coating rough textured surfaces.

**Pack Sizes:** 1 litre, 4 litres, and 20 litres.

#### **Specifications**

##### **New and Unpainted Surfaces:**

No priming is required when coating new or unpainted plaster, cement rendering, fair-faced concrete, brick stone etc. Surface to be painted must be clean, dry and free from grease and other impurities. 3 coats are recommended allowing 4 hours between coats.

##### **Previously Painted Surfaces in Sound Conditions:**

Ensure surface is clean, dry and free from any contamination. No primer is required. However, when recoating on gloss paint, the surface must be abraded with sandpaper to provide a key. Apply a coat of Duracoat Universal Undercoat. Leave to dry for 24 hours and then apply 2 coats of Duracoat Duraplast, allowing 4 hours between coats.

##### **Previously Painted Surfaces in Unsound Conditions:**

Loose, flaking, powdery material must be removed prior to painting. Walls which were previously painted with low grade paint, dampers, white wash, cement paints and lime wash must be completely sanded down to firm base or original plaster. Any surface cracks or holes should be raked out and filled with **Supafix** Crack Filler (**Supafix** Crack Filler is not recommended for external use). Treat surface for mould or algae if present with Duracoat Fugicidal Wash and ensure that the surface is completely dry. Apply at least one coat of Duracoat Penetrating Primer to seal the surface prior to applying Duracoat Duraplast. Insufficient surface preparation and treatment of deteriorated and mould infected surfaces will result in complete failure of the new paint system in a short while.

**Storage:**

Store in a cool and dry place. Close tins tightly and use within 3 months.

North Airport Road, Embakasi, Nairobi. Tel: (020) 6823555/954, 6823955

Email: [customerservice@bascopaints.com](mailto:customerservice@bascopaints.com)

[www.bascopaints.com](http://www.bascopaints.com)

Facebook: BascoProductsKenya

Twitter: @bascopaints